

# VALOX™ RESIN 325

REGION ASIA

## DESCRIPTION

General purpose, unreinforced, improved processing. Applications like sprinklers and nozzles, pumps, door handle, tank covers, pens, pencils etc.

## TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	51	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	200	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	82	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2340	MPa	ASTM D 790
Hardness, Rockwell R	117	-	ASTM D 785
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	1602	J/m	ASTM D 4812
Izod Impact, notched, 23°C	53	J/m	ASTM D 256
Modified Gardner, 23°C	40	J	ASTM D 3029
<b>THERMAL</b>			
HDT, 0.45 MPa, 6.4 mm, unannealed	154	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	54	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.1E-05	1/°C	ASTM E 831
CTE, 60°C to 138°C, flow	1.39E-04	1/°C	ASTM E 831
Relative Temp Index, Elec	120	°C	UL 746B
Relative Temp Index, Mech w/impact	120	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
<b>PHYSICAL</b>			
Specific Gravity	1.31	-	ASTM D 792
Specific Volume	0.76	cm <sup>3</sup> /g	ASTM D 792
Water Absorption, 24 hours	0.08	%	ASTM D 570
Water Absorption, equilibrium, 23C	0.34	%	ASTM D 570
Mold Shrinkage, flow, 0.75-2.3 mm	0.9 – 1.6	%	SABIC method
Mold Shrinkage, flow, 2.3-4.6 mm	1.5 – 2.3	%	SABIC method
Mold Shrinkage, xflow, 0.75-2.3 mm	1 – 1.7	%	SABIC method
Mold Shrinkage, xflow, 2.3-4.6 mm	1.6 – 2.4	%	SABIC method
<b>ELECTRICAL</b>			
Volume Resistivity	>4.E+16	Ohm-cm	ASTM D 257
Dielectric Strength, in air, 3.2 mm	15.7	kV/mm	ASTM D 149
Dielectric Strength, in oil, 1.6 mm	23.2	kV/mm	ASTM D 149
Dielectric Strength, in oil, 3.2 mm	15.7	kV/mm	ASTM D 149
Relative Permittivity, 100 Hz	3.3	-	ASTM D 150
Relative Permittivity, 1 MHz	3.1	-	ASTM D 150
Dissipation Factor, 100 Hz	0.002	-	ASTM D 150
Dissipation Factor, 1 MHz	0.02	-	ASTM D 150

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Arc Resistance, Tungsten {PLC}	4	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	3	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	1	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
<b>FLAME CHARACTERISTICS</b>			
UL Recognized, 94HB Flame Class Rating	0.83	mm	UL 94
UV-light, water exposure/immersion	F1	-	UL 746C
<b>INJECTION MOLDING</b>			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	12	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	245 – 260	°C	
Nozzle Temperature	240 – 255	°C	
Front - Zone 3 Temperature	245 – 260	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 250	°C	
Mold Temperature	50 – 75	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 100	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.013 – 0.025	mm	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.