

# LNPT<sup>™</sup> FARADEx<sup>™</sup> COMPOUND ES003E

EMI-X ES-1003 EM  
REGION AMERICAS

## DESCRIPTION

LNP<sup>®</sup> FARADEx<sup>®</sup> ES003E is a Polyetherimide resin containing 15% Stainless Steel Fibers. Added feature of this grade is: EMI/RFI Shielding.

## TYPICAL PROPERTY VALUES

Revision 20180906

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 5 mm/min	105	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	105	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4.8	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	5	%	ASTM D 638
Tensile Modulus, 50 mm/min	4660	MPa	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	4590	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	99	MPa	ISO 527
Tensile Stress, break, 5 mm/min	98	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4	%	ISO 527
Tensile Strain, break, 5 mm/min	4.3	%	ISO 527
Tensile Modulus, 1 mm/min	4340	MPa	ISO 527
Flexural Stress	155	MPa	ISO 178
Flexural Modulus, 2 mm/min	4310	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	485	J/m	ASTM D 4812
Izod Impact, notched, 23°C	34	J/m	ASTM D 256
Multiaxial Impact	1	J	ISO 6603
Instrumented Impact Total Energy, 23°C	7	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	33	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL</b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	190	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	180	°C	ASTM D 648
CTE, -30°C to 30°C, flow	4.E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	4.4E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	194	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	177	°C	ISO 75/Af
<b>PHYSICAL</b>			
Specific Gravity	1.46	-	ASTM D 792
Density	1.46	g/cm <sup>3</sup>	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.19	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	0.6 – 0.8	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.8 – 1	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.27	%	ISO 62

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>ELECTRICAL</b>			
Volume Resistivity	8.9E+01	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+00 – 3.E+00	Ohm	ASTM D 257
Shielding Effectiveness @ 2.5mm	60	dB	SABIC method

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.