

## LNP<sup>TM</sup> FARADEX<sup>TM</sup> COMPOUND AX88130

EMI-X PDX-A-88130

## **DESCRIPTION**

LNP\* FARADEX\* AX88130 is a compound based on ABS resin containing Stainless Steel Fiber. Added feature of this grade is EMI/RFI Shielding.

## **TYPICAL PROPERTY VALUES**

Revision 20200306

| PROPERTIES                                   | TYPICAL VALUES | UNITS  | TEST METHODS |
|--|----------------|--------|--------------|
| MECHANICAL                                   |                |        |              |
| Tensile Stress, brk, Type I, 5 mm/min        | 52             | MPa    | ASTM D 638   |
| Tensile Strain, brk, Type I, 5 mm/min        | 3 – 4          | %      | ASTM D 638   |
| Flexural Stress, brk, 1.3 mm/min, 50 mm span | 93             | MPa    | ASTM D 790   |
| Flexural Modulus, 1.3 mm/min, 50 mm span     | 3440           | MPa    | ASTM D 790   |
| IMPACT                                       |                |        |              |
| Izod Impact, unnotched, 23°C                 | 160 – 214      | J/m    | ASTM D 4812  |
| Izod Impact, notched, 23°C                   | 58             | J/m    | ASTM D 256   |
| THERMAL                                      |                |        |              |
| HDT, 1.82 MPa, 3.2mm, unannealed             | 93             | °C     | ASTM D 648   |
| PHYSICAL                                     |                |        |              |
| Specific Gravity                             | 1.13           | -      | ASTM D 792   |
| Moisture Absorption, 50% RH, 24 hrs          | 0.3            | %      | ASTM D 570   |
| Mold Shrinkage, 48 hrs @ 23°C, flow          | 0.5 – 0.5      | %      | SABIC method |
| ELECTRICAL                                   |                |        |              |
| Surface Resistivity                          | 1.E+03         | Ohm    | ASTM D 257   |
| Volume Resistivity                           | 1.E+03         | Ohm-cm | IEC 60093    |
| INJECTION MOLDING                            |                |        |              |
| Drying Temperature                           | 80             | °C     |              |
| Drying Time                                  | 4              | hrs    |              |
| Maximum Moisture Content                     | 0.05 – 0.1     | %      |              |
| Melt Temperature                             | 260            | °C     |              |
| Front - Zone 3 Temperature                   | 265 – 275      | °C     |              |
| Middle - Zone 2 Temperature                  | 230 – 245      | °C     |              |
| Rear - Zone 1 Temperature                    | 205 – 215      | °C     |              |
| Mold Temperature                             | 70 – 80        | °C     |              |
| Back Pressure                                | 0.2 – 0.3      | MPa    |              |
| Screw Speed                                  | 30 - 60        | rpm    |              |

## **DISCLAIMER**

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.